

New Sheet

A step of mixing 1) a particulate elastomer selected from polybutadiene modified with carboxyl group, polyisoprene modified with carboxyl group or styrene/butadiene copolymer modified with carboxyl group with 2) a carbonaceous material comprising activated carbon as an active material thereby obtaining a powdery mixture, wherein the particulate elastomer is in a concentration of 2 to 10 parts by weight per 100 parts by weight of the combination of the particulate elastomer and the carbonaceous material



A step of dry-forming the resulting powdery mixture

FIGURE 1